



IMRON® MARINE TH39 Water Based degreaser

Description

Mixture of water and solvents developed for cleaning and degreasing before surface preparation and before application of primers or topcoats.
Composition based on water and glycol ethers.

Products

TH39 Water Based degreaser

Properties

- Eliminates contaminants from old finishes and prepared areas to obtain a perfectly cleaned surface before the application of a primer or topcoat.

Application - remarks

Following specifications listed in the Imron® Marine Manual and in particular:

- Degrease the sanded surface with TH39 just before application of primer or topcoat.
- Wipe dry with clean cloth.
- Never let TH39 evaporate from the surface. Treat only one small area at the time.
- Do not use TH39 to degrease wash primer.
- Use only on fully cured surfaces.
- Change cloths often; never use dirty clothes.

RECOMMENDED USE

Products	Packages	Storability at 20°C	VOC	Density	Flash Point
	(l)	(Months)	(g/l)	(kg/l)	(°C)
TH39	5	60	± 5 194	± 0.01 0.977	68



IMRON® MARINE TH39 Water Based degreaser

Safety

Consult Material Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

Information

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

This Technical Data Sheet supersedes all previous issues.

Copyright© 2015, Axalta Coating Systems, LLC and all affiliates. All rights reserved. The Axalta logo, Axalta™, Axalta Coating Systems™ and all products denoted with™ or® are trademarks or registered trademarks of Axalta Coating Systems, LLC and its affiliates. Axalta trademarks may not be used in connection with any product or service that is not an Axalta product or service.